



COLLECTION | BRUSHED & OILED COLOR | NORMAN BREEZE

Wood species | Ash
Grade | 1 Common
Constructions | 3-layer T&G Engineered Flooring
Size | 19,05 x 127 x 600...2100 mm (¾" x 5" x 2'..7")
Finish | Silk finish

CONSTRUCTION : 3-LAYER T&G ENGINEERED FLOORING

DIMENSIONS :			PACKAGING :		
			BOX	PALLET	
Thickness	19,05 mm (¾")		Content:	2,0 m ²	36 (72,0 m ²)
Width	127 mm (5")		Weight	25 kg	927 kg
Length	600 ...2100 mm (2'..7')		H x W x L	85 x 280 x 2153 mm	1140 x 845 x 2160 mm
Average length	1,0 m (3 ⅓')		Content:	21,52 sq.ft.	774,72 sq.ft.
Microbevel	0,5 mm		Weight	56 lb	2051 lb
Joint type	tongue and groove (T&G)	H x W x L	3" x 11" x 85"	45" x 33" x 85"	

DEVIATIONS :

Deviation on Thickness	± 0,2 mm	EN 13489 ГОСТ 862.3
Deviation on Width	± 0,2 mm	
Height Difference	≤ 0,2 % of width	
Cup	≤ 0,2 % of plank width	EN 13489
Spring	≤ 0,1 % of length	
Bow	≤ 0,5 % of length	

CHARACTERISTICS :

Fire resistance	Dfl-s1	EN 14342
Formaldehyde emission class	E1	
Pentachlorophenol content	None	
Thermal resistance	0,118 m ² ·K/W	
Thermal conductivity	0,161 W/(m·K)	
Structural warranty	Lifetime	

INSTALLATION :



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

STORAGE AND USAGE :



— Air humidity 40% – 65%
— Temperature +18 °C – +22 °C

FINISH : SILK FINISH

DESCRIPTION :	
Type of coating	UV-cured modified polyurethane-acrylate
Surface (finish) type	Semi-closed pores, wire brushed
Sheen	Silk matte 9-18 GU/85°
Finish warranty	-

CLASSIFICATION SURFACE CHARACTERISTICS :

Wear resistance	Not rated	EN 438-2
Scratch resistance	Not rated	EN 438
Slip resistance	50 (SRV dry)	EN 15676
Resistance to chemical agents	Class 5 (Except blue ink)	EN 13442
Repairability	Medium	

MAINTENANCE AND CARE CONDITIONS :

Maintenance of hardwood floors with Silk finish assumes regular (daily if necessary) cleaning from dust and grit using a vacuum, followed by a thorough cleaning with Coswick Hardwood Floor Cleaner or other similar product. Floor surface areas that receive the most traffic and get worn down quicker, such as areas by the front door, hallways, kitchens etc., should be periodically renewed with special Coswick Restorative Oil. This product restores the protective surface film. Frequency of use depends on type of interior and intensity of foot traffic. For residential interiors, restorative cleaning should be done once in 3-5 years; for public and commercial interiors with intense foot traffic, it is recommended to use the product 2-4 times a year.

GRADE : 1 COMMON

DESCRIPTION :		DESCRIPTION :	
Sound sapwood	Permitted contrast to 25% of the plank area	Bark pocket	Permitted up to 50 mm in length, up to 5 mm in width, filled
Colour variation	No limit	Pith	Permitted
Knot	Permitted up to 25 mm, filled	Slope of grain	Permitted
Crecks	Permitted narrow, filled	Medullary ray	Permitted