



COLLECTION | CLASSIC
COLOR | FOGGY DAWN

Wood species | American Walnut
Grade | 1 Natur
Constructions | 3-layer T&G Engineered Flooring
Size | 19,05 x 190 x 600...2100 mm (3/4" x 7 1/2" x 2'..7')
Finish | Silk mat finish

CONSTRUCTION : 3-LAYER T&G ENGINEERED FLOORING

DIMENSIONS :			PACKAGING :	
			BOX	PALLET
Thickness	19,05 mm (3/4")		Content: 1,86m ²	40 (74,4 m ²)
Width	190 mm (7 1/2)		Weight: 23 kg	950 kg
Length	600 ...2100 mm (2'..7')		H x W x L 95 x 225 x 2150 mm	1120 x 905 x 2160 mm
Average length	0,89 m (3')		Content: 20,01 sq.ft.	800,40 sq.ft.
Microbevel	0,5 mm		Weight: 51 lb	2100 lb
Joint type	tongue and groove (T&G)	H x W x L 4" x 10" x 85"	44" x 36" x 85"	

DEVIATIONS :

Deviation on Thickness	± 0,2 mm	EN 13489 ГОСТ 862.3 СТБ 2121
Deviation on Width	± 0,2 mm	
Height Difference	≤ 0,2 % of width	
Cup	≤ 0,2 % of plank width	EN 13489
Bow	≤ 0,1 % of length	
Spring	≤ 0,5 % of length	

CHARACTERISTICS :

Fire resistance	Dfl-s1	EN 14342
Formaldehyde emission class	E1	
Pentachlorophenol content	None	
Thermal resistance	0,118 m ² ·K/W	
Thermal conductivity	0,161 W/(m·K)	
Structural warranty	Lifetime	

INSTALLATION :



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor.
Applicable above, on and below ground level.

STORAGE AND USAGE :



— Air humidity 40% – 65%
— Temperature +18 °C – +22 °C

FINISH : SILK MAT FINISH

DESCRIPTION :	
Type of coating	UV-cured modified polyurethane-acrylate
Surface (finish) type	Semi-closed pores, wire brushed
Sheen	Matte 2-7 GU/60°
Finish warranty	-

CLASSIFICATION SURFACE CHARACTERISTICS :

Wear resistance	Not rated	EN 438-2
Scratch resistance	Not rated	EN 438
Slip resistance	50 (SRV dry)	EN 15676
Resistance to chemical agents	Class 5 (Except blue ink)	EN 13442
Repairability	Medium	

MAINTENANCE AND CARE CONDITIONS :

Maintenance of hardwood floors with Silk finish assumes regular (daily if necessary) cleaning from dust and grit using a vacuum, followed by a thorough cleaning with Coswick Hardwood Floor Cleaner or other similar product. Floor surface areas that receive the most traffic and get worn down quicker, such as areas by the front door, hallways, kitchens etc., should be periodically renewed with special Coswick Restorative Oil. This product restores the protective surface film. Frequency of use depends on type of interior and intensity of foot traffic. For residential interiors, restorative cleaning should be done once in 3-5 years; for public and commercial interiors with intense foot traffic, it is recommended to use the product 2-4 times a year.

GRADE : 1 NATUR

DESCRIPTION :		DESCRIPTION :	
Sound sapwood	No limit	Bark pocket	Permitted up to 50 mm in length, up to 5 mm in width, filled
Colour variation	No limit	Pith	Permitted
Knot	Permitted up to 35 mm, filled	Slope of grain	Permitted
Checks	Permitted filled up to 1 mm in width	Medullary ray	Permitted