



COLLECTION | COUNTRY COLOR | DARK CHOCOLATE

Wood species | Oak
Grade | Tavern
Constructions | Solid Hardwood Flooring
Size | 19,05 x 127 x 300...1845 mm (¾" x 5" x 1'..6")
Finish | Silk Oil

CONSTRUCTION : SOLID HARDWOOD FLOORING

DIMENSIONS :			PACKAGING :	
			BOX	PALLET
Thickness	19,05 mm (¾")		Content: 1,78 m ²	36 (64,08 m ²)
Width	127 mm (5")		Weight 24 kg	874 kg
Length	300 ...1845 mm (1'..6')		H x W x L 85 x 280 x 1900 mm	1140 x 845 x 1900 mm
Average length	0,74 m (2 ½')		Content: 19,15 sq.ft.	689,40 sq.ft.
Microbevel	0,5 mm		Weight 53 lb	1930 lb
Joint type	tongue and groove (T&G)		H x W x L 3" x 11" x 75"	45" x 33" x 75"

DEVIATIONS :

Deviation on Thickness	± 0,2 mm	EN 13226 ГОСТ 862.1 СТБ 1454
Deviation on Width	± 0,2 mm	
Height Difference	≤ 0,2 % of width	
Cup	≤ 0,2 % of plank width	EN 13226
Bow	≤ 0,5 % of length	
Spring	≤ 0,5 ‰ of length	

CHARACTERISTICS :

Fire resistance	Dfl-s1	EN 14342
Formaldehyde emission class	E1	
Pentachlorophenol content	None	
Thermal resistance	0,112 m ² ·K/W	
Thermal conductivity	0,170 W/(m·K)	
Structural warranty	Lifetime	

INSTALLATION :



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor.
Applicable above and on ground level.

STORAGE AND USAGE :



— Air humidity 45% – 55%
— Temperature +18 °C – +22 °C

FINISH : SILK OIL

DESCRIPTION :	
Type of coating	UV-cured modified polyurethane-acrylate
Surface (finish) type	Semi-closed pores, wire brushed
Sheen	Silk matte 9-18 GU/85°
Finish warranty	-

CLASSIFICATION SURFACE CHARACTERISTICS :

Wear resistance	Not rated	EN 438-2
Scratch resistance	Not rated	EN 438
Slip resistance	50 (SRV dry)	EN 15676
Resistance to chemical agents	Class 5 (Except blue ink)	EN 13442
Repairability	Medium	

MAINTENANCE AND CARE CONDITIONS :

Maintenance of hardwood floors with Silk Oil finish assumes regular (daily if necessary) cleaning from dust and grit using a vacuum, followed by a thorough cleaning with Coswick Hardwood Floor Cleaner or other similar product. Floor surface areas that receive the most traffic and get worn down quicker, such as areas by the front door, hallways, kitchens etc., should be periodically renewed with special Coswick Restorative Oil. This product restores the protective surface film. Frequency of use depends on type of interior and intensity of foot traffic. For residential interiors, restorative cleaning should be done once in 3-5 years; for public and commercial interiors with intense foot traffic, it is recommended to use the product 2-4 times a year.

GRADE : TAVERN

DESCRIPTION :		DESCRIPTION :	
Sound sapwood	No limit	Bark pocket	No limit (after filling)
Colour variation	No limit	Pith	Permitted
Knot	No limit (after filling)	Slope of grain	Permitted
Checks	Permitted filled up to 3 mm in width	Medullary ray	Permitted