



COLLECTION | HERITAGE COLOR | PASTEL

Wood species | Oak
Grade | 1 Common
Constructions | Solid Hardwood Flooring
Size | 19,05 x 127 x 300...1845 mm (3/4" x 5" x 1'..6")
Finish | Silk Oil

CONSTRUCTION : SOLID HARDWOOD FLOORING

| DIMENSIONS : | | | PACKAGING : | |
|----------------|-------------------------|-----------|---------------------|----------------------------|
| | | | BOX | PALLET |
| Thickness | 19,05 mm (3/4") | Content: | 1,78 m ² | 36 (64,08 m ²) |
| Width | 127 mm (5") | Weight | 24 kg | 874 kg |
| Length | 300 ...1845 mm (1'..6') | H x W x L | 85 x 280 x 1900 mm | 1140 x 845 x 1900 mm |
| Average length | 0,74 m (2 1/2') | Content: | 19,15 sq.ft. | 689,40 sq.ft. |
| Microbevel | 0,5 mm | Weight | 53 lb | 1930 lb |
| Joint type | tongue and groove (T&G) | H x W x L | 3" x 11" x 75" | 45" x 33" x 75" |

| DEVIATIONS : | | |
|------------------------|------------------------|------------------------------------|
| Deviation on Thickness | ± 0,2 mm | EN 13226 ГОСТ 862.1 СТБ 1454 |
| Deviation on Width | ± 0,2 mm | |
| Height Difference | ≤ 0,2 % of width | |
| Cup | ≤ 0,2 % of plank width | EN 13226 |
| Bow | ≤ 0,5 % of length | |
| Spring | ≤ 0,5 ‰ of length | |

| CHARACTERISTICS : | | |
|-----------------------------|---------------------------|----------|
| Fire resistance | Dfl-s1 | EN 14342 |
| Formaldehyde emission class | E1 | |
| Pentachlorophenol content | None | |
| Thermal resistance | 0,112 m ² ·K/W | |
| Thermal conductivity | 0,170 W/(m·K) | |
| Structural warranty | Lifetime | |

| INSTALLATION : | STORAGE AND USAGE : |
|---|---|
| <p>Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above and on ground level.</p> | <p>— Air humidity 45% – 55% — Temperature +18 °C – +22 °C</p> |

FINISH : SILK OIL

| DESCRIPTION : | |
|-----------------------|---|
| Type of coating | UV-cured modified polyurethane-acrylate |
| Surface (finish) type | Semi-closed pores, wire brushed |
| Sheen | Silk matte 9-18 GU/85° |
| Finish warranty | - |

| CLASSIFICATION SURFACE CHARACTERISTICS : | | |
|--|---------------------------|----------|
| Wear resistance | Not rated | EN 438-2 |
| Scratch resistance | Not rated | EN 438 |
| Slip resistance | 50 (SRV dry) | EN 15676 |
| Resistance to chemical agents | Class 5 (Except blue ink) | EN 13442 |
| Repairability | Medium | |

MAINTENANCE AND CARE CONDITIONS :

Maintenance of hardwood floors with Silk Oil finish assumes regular (daily if necessary) cleaning from dust and grit using a vacuum, followed by a thorough cleaning with Coswick Hardwood Floor Cleaner or other similar product. Floor surface areas that receive the most traffic and get worn down quicker, such as areas by the front door, hallways, kitchens etc., should be periodically renewed with special Coswick Restorative Oil. This product restores the protective surface film. Frequency of use depends on type of interior and intensity of foot traffic. For residential interiors, restorative cleaning should be done once in 3-5 years; for public and commercial interiors with intense foot traffic, it is recommended to use the product 2-4 times a year.

GRADE : 1 COMMON

| DESCRIPTION : | | DESCRIPTION : | |
|------------------|---|----------------|--|
| Sound sapwood | Permitted contrast to 25% of the plank area | Bark pocket | Permitted up to 50 mm in length, up to 5 mm in width, filled |
| Colour variation | No limit | Pith | Permitted |
| Knot | Permitted up to 25 mm, filled | Slope of grain | Permitted |
| Checks | Permitted filled up to 0,5 mm in width | Medullary ray | Permitted |