



COLLECTION | HERRINGBONE COLOR | NATURAL

Wood species | American Walnut
Grade | Select & Better
Constructions | 3-layer T&G Engineered Flooring
Size | 15 x 107,95 x 647,7 mm (5/8" x 4 1/4" x 25 1/2")
Finish | Lacquer finish

CONSTRUCTION : 3-LAYER T&G ENGINEERED FLOORING

| DIMENSIONS : | | | PACKAGING : | | |
|--------------|-------------------------|-----------|----------------|--------------------|---------------------------|
| | | | BOX | PALLET | |
| Thickness | 15 mm (5/8") | | Content: | 2,1 m ² | 42 (88,2 m ²) |
| Width | 107,95 mm (4 1/4") | | Weight | 22 kg | 923 kg |
| Length | 647,7 mm (25 1/2") | | H x W x L | 151 x 338 x 675 mm | 1061 x 680 x 2020 mm |
| Cut angle | 90° | | Content: | 22,59 sq.ft. | 949,03 sq.ft. |
| Microbevel | 0,5 mm | | Weight | 49 lb | 2042 lb |
| Joint type | tongue and groove (T&G) | H x W x L | 6" x 14" x 27" | 42" x 27" x 80" | |

DEVIATIONS :

| | | |
|------------------------|------------------------|------------------------|
| Deviation on Thickness | ± 0,2 mm | EN 13489 ГОСТ 862.3 |
| Deviation on Width | ± 0,2 mm | |
| Height Difference | ≤ 0,2 % of width | |
| Cup | ≤ 0,2 % of plank width | EN 13489 |
| Spring | ≤ 0,1 % of length | |
| Bow | ≤ 0,5 % of length | |

CHARACTERISTICS :

| | | |
|-----------------------------|---------------------------|----------|
| Fire resistance | Dfl-s1 | EN 14342 |
| Formaldehyde emission class | E1 | |
| Pentachlorophenol content | None | |
| Thermal resistance | 0,095 m ² ·K/W | |
| Thermal conductivity | 0,158 W/(m·K) | |
| Structural warranty | Lifetime | |

INSTALLATION :



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor.
Applicable above, on and below ground level.

STORAGE AND USAGE :



— Air humidity 40% – 65%
— Temperature +18 °C – +22 °C

FINISH : LACQUER FINISH

| DESCRIPTION : | |
|-----------------------|--|
| Type of coating | UV-curable polyurethane-acrylate with micro-corundum |
| Surface (finish) type | Closed pores |
| Sheen | Semigloss 30-40 GU/60° |
| Finish warranty | 25 years |

CLASSIFICATION SURFACE CHARACTERISTICS :

| | | |
|-------------------------------|--|----------|
| Wear resistance | Taber Test - 500 turns (S 42; 1000 gr) | EN 438-2 |
| Scratch resistance | Rating 3 | EN 438 |
| Slip resistance | 46 (SRV dry) | EN 15676 |
| Resistance to chemical agents | Class 5 (Except blue ink) | EN 13442 |
| Repairability | Low | |

MAINTENANCE AND CARE CONDITIONS :

Maintenance of hardwood floors with lacquer CosNanoTech+ finish assumes regular (daily if necessary) cleaning from dust and dirt using a vacuum, followed by a thorough cleaning using Coswick hardwood floor cleaner or other similar product. Due to high wear resistance properties, CosNanoTech+ lacquer finish does not require any additional care or finish renewal throughout the entire life of the floor.

GRADE : SELECT & BETTER

| DESCRIPTION : | | DESCRIPTION : | |
|------------------|---|----------------|--|
| Sound sapwood | Permitted non-contrasting up to 25% of the plank area | Bark pocket | Permitted up to 10 mm in length, up to 3 mm in width, filled |
| Colour variation | Permitted slight colour variation | Pith | Permitted healthy heart |
| Knot | Permitted up to 10 mm, filled | Slope of grain | Permitted |
| Crecks | Not permitted | Medullary ray | Permitted |