



**COLLECTION | MOSAIC FLOORS**  
**COLOR | NATURAL**  
 Wood species | American Walnut  
 Grade | Traditional  
 Pattern | Langeais  
 Constructions | 2-layer T&G  
 Size | 19,05 x 635 x 635 mm (¾" x 25" x 25")  
 Finish | Resilient Lacquer

## CONSTRUCTION : 2-LAYER T&G

DIMENSIONS :			PACKAGING :		
			BOX	PALLET	
Thickness	19,05 mm (¾")		Content:	1,61 m <sup>2</sup>	27 (43,47 m <sup>2</sup> )
Width	635 mm (25")		Weight	21 kg	602 kg
Length	635 mm (25")		H x W x L	85 x 648 x 660 mm	900 x 680 x 1960 mm
Average length	-		Content:	17,32 sq.ft.	467,64 sq.ft.
Microbevel	1,0 mm		Weight	49 lb	1332 lb
Joint type	tongue and groove (T&G)	H x W x L	3" x 26" x 26"	35" x 27" x 77"	

## DEVIATIONS :

Deviation on Thickness	± 0,2 mm	EN 13489 ГОСТ 862.3 СТБ 2121
Deviation on Width	± 0,3 mm	
Height Difference	≤ 0,04 % of width	
Cup	≤ 0,2 % of plank width	EN 13489
Bow	-	
Spring	≤ 0,5 % of length	

## CHARACTERISTICS :

Fire resistance	Dfl-s1	EN 14342
Formaldehyde emission class	E1	
Pentachlorophenol content	None	
Thermal resistance	0,128 m <sup>2</sup> ·K/W	
Thermal conductivity	0,148 W/(m·K)	
Structural warranty	Lifetime	

## INSTALLATION :



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor.  
Applicable above, on and below ground level.

## STORAGE AND USAGE :



— Air humidity 40% – 65%  
— Temperature +18 °C – +22 °C

## FINISH : RESILIENT LACQUER

DESCRIPTION :	
Type of coating	UV-cured modified polyurethane-acrylate
Surface (finish) type	Semi-closed pores
Sheen	Semigloss 15 - 22 GU/60°
Finish warranty	-

## CLASSIFICATION SURFACE CHARACTERISTICS :

Wear resistance	Not rated	EN 438-2
Scratch resistance	Not rated	EN 438
Slip resistance	52 (SRV dry)	EN 15676
Resistance to chemical agents	Class 5 (Except blue ink)	EN 13442
Repairability	Medium	

## MAINTENANCE AND CARE CONDITIONS :

Maintenance of hardwood floors with Resilient Lacquer finish assumes regular (daily if necessary) cleaning from dust and dirt using a vacuum, followed by a thorough cleaning using Coswick hardwood floor cleaner or other similar product.

## GRADE : TRADITIONAL

DESCRIPTION :		DESCRIPTION :	
Sound sapwood	Permitted contrast to 25% of the plank area	Bark pocket	Permitted up to 50 mm in length, up to 5 mm in width, filled
Colour variation	No limit	Pith	Permitted
Knot	Permitted up to 25 mm, filled	Slope of grain	Permitted
Checks	Permitted filled up to 0,5 mm in width	Medullary ray	Permitted