





PLANK HARDWOOD FLOORING | TECHNICAL INFORMATION

Product # 1154-4526-30



DARK WOOD COLLECTION DECOR | LONDON

Wood species | Oak
Selection | Tavern
Constructions | 3-layer flooring T&G
Size | 19,05x127x600...2100 mm (3/4"x5"x2'...7')
Finish | Silk mat finish

CONSTRUCTION: 3-LAYER FLOORING T&G

| DIMENSIONS : | | | PACKAGING : | |
|----------------|----------------------|-----------|---------------------|-----------------------------|
| | | | BOX | PALLET |
| Thickness | 19,05 mm (3/4") | Content | 2 m ² | 36 box (72 m ²) |
| Width | 127 mm (5") | Weigh | 25 kg | 917 kg |
| Length | 600...2100 (2'...7') | H x W x L | 90 x 275 x 2 155 mm | 1156 x 846 x 2 163 mm |
| Average length | 0.98 m (3 1/4') | Content | 21,520 sq.ft. | 774,720 sq.ft. |
| Microlevel | 0,5 mm | Weigh | 26 lb | 929 lb |
| Joint type | T&G | H x W x L | 4" x 11" x 85" mm | 46" x 33" x 86" mm |

DEVIATIONS:

| | | |
|------------------------|---------------------------|------------------------|
| Deviation on Thickness | ± 0,2 mm | EN 13489 FOCT 862.3 |
| Deviation on Width | ± 0,2 mm | |
| Height Difference | ≤ 0,2 mm on 100 mm length | |
| Cup | ≤ 0,2 % of width | EN 13489 |
| Bow | ≤ 0,5 % of length | |
| Spring | ≤ 0,1 % of length | |

CHARACTERISTICS:

| | | |
|-----------------------------|--------------------------|----------|
| Fire resistance | Dfl-s1 | EN 14342 |
| Formaldehyde emission class | E1 | |
| Pentachlorophenol content | None | |
| Thermal resistance | 0,082 m ² K/W | |
| Thermal conductivity | 0,161 W/(m·K) | |
| Structural warranty | Lifetime | |

УСТАНОВКА:



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

УСЛОВИЯ ЭКСПЛУАТАЦИИ И ХРАНЕНИЯ:



— Air humidity 40% – 65%
— Temperature +18 °C – +22 °C

FINISH : SILK MAT FINISH

| DESCRIPTION : | |
|-----------------------|---|
| Type of coating | UV-cured modified polyurethane-acrylate |
| Surface (finish) type | Semi-closed pores, wire brushed |
| Sheen | Matte, 2-7 GU/60° |
| Finish warranty | - |

CLASSIFICATION SURFACE CHARACTERISTICS:

| | | |
|-------------------------------|---------------------------|----------|
| Wear resistance | Not rated | EN 438-2 |
| Scratch resistance | Not rated | EN 438 |
| Slip resistance | 50 (SRV dry) | EN 15676 |
| Resistance to chemical agents | Class 5 (Except blue ink) | EN 13442 |
| Repairability | Medium | |

MAINTENANCE AND CARE CONDITIONS :

Maintenance of hardwood floors with Silk finish assumes regular (daily if necessary) cleaning from dust and grit using a vacuum, followed by a thorough cleaning with Coswick Hardwood Floor Cleaner or other similar product. Floor surface areas that receive the most traffic and get worn down quicker, such as areas by the front door, hallways, kitchens etc., should be periodically renewed with special Coswick Restorative Oil. This product restores the protective surface film. Frequency of use depends on type of interior and intensity of foot traffic. For residential interiors, restorative cleaning should be done once in 3-5 years; for public and commercial interiors with intense foot traffic, it is recommended to use the product 2-4 times a year.

GRADE : TAVERN

| DESCRIPTION: | | DESCRIPTION: | |
|------------------|-------------------------------------|----------------|--------------------------|
| Sound sapwood | Up to 25% of board width is allowed | Bark pocket | No limit (after filling) |
| Colour variation | Moderate contrast allowed | Pith | Permitted |
| Knot | Permitted big, filled | Slope of grain | Permitted |
| Cracks | Permitted wide, filled | Medullary ray | Permitted |

COSWICK Ltd.

2B Kolasa Str., 223034 Zaslavi, Republic of Belarus
Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com
www.coswick.com

