
# MOSAIC WOOD FLOORS FLOORS I TECHNICAL INFORMATION

Product # 1197-1591-10

COSWICK
Solid Hardwood Floors






**GREY SHADOW COLLECTION**
**DECOR |** PAYNE'S GREY

**Wood species |** Oak
**Selection |** Select & Better
**Pattern |** Tile
**Constructions |** 3-layer flooring T&G
**Size |** 15x190x220 mm (5/8"x7 1/2"x8 5/8")
**Finish |** Silk mat finish

## CONSTRUCTION: 3-LAYER FLOORING T&G

| DIMENSIONS : | |
|---|---|
| Thickness | 15 mm (5/8") |
| Width | 190 mm (7 1/2") |
| Length | 220 mm (8 5/8") |
| Microbevel | 0,5 mm |
| Joint type | T&G |




| PACKAGING : | BOX | PALLET |
|---|---|---|
| Content | 1,634 m2 | 40 box (65,36 m2) |
| Weigh | 17 kg | 694 kg |
| H x W x L | 195 x 405 x 470 mm | 1113 x 800 x 1 880 mm |
| Content | 17,582 sq.ft. | 703,274 sq.ft. |
| Weigh | 17 lb | 718 lb |
| H x W x L | 8" x 16" x 22" mm | 44" x 32" x 74" mm |

| DEVIATIONS: | | |
|---|---|---|
| Deviation on Thickness | ± 0,2 mm | |
| Deviation on Length | ± 0,3 mm | EN 13489 |
| Deviation on Width | ± 0,2 mm | ГОСТ 862.3 |
| Angle deviation of planks | ≤ 0,25 mm | |
| Cup | ≤ 0,2 % of width | |
| Bow | ≤ 0,5 % of length | EN 13489 |
| Spring | ≤ 0,1 % of length | |


| CHARACTERISTICS: | | |
|---|---|---|
| Fire resistance | Dfl-s1 | |
| Formaldehyde emission class | E1 | |
| Pentachlorophenol content | None | EN 14342 |
| Thermal resistance | 0,095 m2 K/W | |
| Thermal conductivity | 0,158 W/(m·K) | |
| Structural warranty | Lifetime | |

**УСТАНОВКА:**



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

**УСЛОВИЯ ЭКСПЛУАТАЦИИ И ХРАНЕНИЯ:**




— Air humidity 40% – 65%
— Temperature +18 °C – +22 °C

## FINISH : SILK MAT FINISH

| DESCRIPTION : | |
|---|---|
| Type of coating | UV-cured modified polyurethane-acrylate |
| Surface (finish) type | Semi-closed pores, wire brushed |
| Sheen | Matte, 2–7 GU/60° |
| Finish warranty | - |

| CLASSIFICATION SURFACE CHARACTERISTICS: | | |
|---|---|---|
| Wear resistance | Not rated | EN 438-2 |
| Scratch resistance | Not rated | EN 438 |
| Slip resistance | 50 (SRV dry) | EN 15676 |
| Resistance to chemical agents | Class 5 (Except blue ink) | EN 13442 |
| Repairability | Medium | |

**MAINTENANCE AND CARE CONDITIONS :**

Maintenance of hardwood floors with Silk finish assumes regular (daily if necessary) cleaning from dust and grit using a vacuum, followed by a thorough cleaning with Coswick Hardwood Floor Cleaner or other similar product. Floor surface areas that receive the most traffic and get worn down quicker, such as areas by the front door, hallways, kitchens etc., should be periodically renewed with special Coswick Restorative Oil. This product restores the protective surface film. Frequency of use depends on type of interior and intensity of foot traffic. For residential interiors, restorative cleaning should be done once in 3-5 years; for public and commercial interiors with intense foot traffic, it is recommended to use the product 2-4 times a year.

## GRADE : SELECT & BETTER

| DESCRIPTION: | | DESCRIPTION: | |
|---|---|---|---|
| Sound sapwood | Non-contrasting sapwood is allowed up to 25% of plank area | Bark pocket | Permitted up to 10 mm in lenght, up to 3 mm in width, filled |
| Colour variation | Permitted slight colour variation | Pith | Permitted healthy heart |
| Knot | Permitted up to 10 mm, filled | Slope of grain | Permitted |
| Crecks | Not permitted | Medullary ray | Permitted |

**COSWICK Ltd.**
2B Kolasa Str., 223034 Zaslavl, Republic of Belarus
Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com
**www.coswick.com**

nwfa National Wood Flooring Association · ECO FRIENDLY No added formaldehyde · CTB ISO 9001 · TP BY · CE